

**OTTOSEAL®****S 105****Technical Datasheet****1-component silicone sealant based on acetate**

For indoor and outdoor application

**Characteristic:**

- **Contains fungicides**  
Resistance to mould infestation
- **Excellent weathering, ageing and UV-resistance**  
For long-lasting indoor and outdoor applications

**Fields of application:**

- Expansion joints in connection joints in the floor and wall area
- Expansion joints in bathroom areas
- Sealing double-glazings (e. g. "Profilit")

**Standards and tests:**

- Tested according to EN 15651 – Part 1: F EXT-INT CC 25 LM
- Tested according to EN 15651 – Part 2: G CC 25 LM
- Tested according to EN 15651 – Part 3: XS 1
- Suitable for applications according to IVD instruction sheet no. 3-1+3-2+14+31+35 (IVD = German industry association sealants)
- Quality seal of the IVD (Industrial association for sealants, registered society), tested by the ift Rosenheim (Institute of window engineering, registered society)
- According to regulation (EG) no. 1907/2006 (REACH)
- Classification according to building certification systems, see the sustainability data sheet
- French VOC-emission class A+
- Declaration in "baubook" Austria
- EMICODE® EC 1 Plus - very low emission
- Tested fire behaviour in accordance with EN 13501: class E

**Important information:**

EMICODE® is a registered trademark of GEV e. V. (Düsseldorf, Germany)

Before applying this product the user has to ensure that the materials in the area of contact (solid, liquid and gaseous) are compatible with it and also amongst each other and do not damage or alter (e. g. discolour) each other. As for the materials that will be used at a later stage in the surrounding area of the product the user has to clarify beforehand that the substances of content or evaporations do not lead to an impairment or alteration (e. g. discolouration) of the product. In case of doubt the user should consult the respective manufacturer of the material.

While curing small amounts of acetic acid are released.

Ensure good ventilation during application and curing.

The required vulcanization time prolongs with increasing thickness of the silicone layer. One-component silicones are not suitable for full-area bonding, unless there are specific structural conditions that require such full-area application. If one-component silicones are to be used for thickness layers of more than 15 mm please contact our technical department beforehand.

Avoid contact with materials which contain bitumen and which release solvents, e. g. butyl, EPDM, neoprene, insulating- and bituminous paint.

Upon restoring of joints contaminated with mould the existing elastic sealant must be removed completely. Before re-jointing, the affected jointing areas are to be treated with OTTO Anti-Mildew Spray to remove possibly existing fungal spores. Otherwise a new mould attack may occur in the joints again,

despite the mould protection technology of the sealant.

#### Technical properties:

Skin-forming time at 23 °C/50 % RH [minutes]	~ 15
Curing in 24 hours at 23 °C/50 % RH [mm]	~ 2 - 3
Processing temperature from/to [°C]	+ 5 / + 35
Viscosity at 23 °C	pasty, stable
Density at 23 °C according to ISO 1183-1 [g/cm³]	~ 1,0
Shore-A-hardness according to ISO 868	~ 20
Permissible movement capability [%]	25
Class according to ISO 11600 F	25 LM
Stress expansion modulus at 100 % according to ISO 37, type 3 [N/mm²]	~ 0,3
Tensile expansion according to ISO 37, type 3 [%]	~ 700
Tensile strength according to ISO 37, type 3 [N/mm²]	~ 1,4
Temperature resistance from/to [°C]	- 40 / + 180
Extrusion rate according to ISO 8394-1 [g/min.]	~ 130 - 170
Shrinkage of volume according to ISO 10563 [%]	< 10
Shelf life at 23 °C/50 % RH for cartridge/foil bag [months]	15

These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications.

#### Pretreatment:

The adherent surfaces have to be clean, free from fat, dry and sustainable.

All adherent surfaces must be clean and any contaminant such as release agents, preserving agents, grease, oil, dust, water, old adhesives or sealants and other substances which could affect adhesion, should be removed. Cleaning of non-porous substrates: Apply OTTO Cleaner T (airing time approx. 1 minute) using a clean, lint-free cotton cloth. Cleaning porous substrates: Clean surfaces with steel-wire brush e. g. or a grinding disk to remove loose particles.

#### Primer Table:

The demands on elastic sealings and bondings depend on the respective exterior influences. Extreme fluctuations in temperature, tensile or shear forces, repeated contact with water etc. demand high requirements of a bonding. In such cases it is advisable to apply primer according to the recommendations of our technical department (e. g. +/OTTO Primer 1216) in order to achieve a resilient bonding.

Acrylic glass/PMMA	-
Acrylic bathroom surfaces (e. g. bath tubs)	+ / 1101
Aluminium	+
Aluminium anodized	1216
Aluminium powder-coated	1101 / T
Aluminium powder-coated (contains teflon)	T
Concrete	1105
Concrete block	-
Lead	-
Chrome	1216
Stainless steel	1216
Iron	-
Epoxid resin coating	T
Fibre cement	1105
Glass	+ / 1226
Wood, painted (solvent systems)	+
Wood, painted (aqueous systems)	+ / 1216
Wood, varnished (solvent systems)	1216
Wood, varnished (aqueous systems)	1215 / 1226
Wood, untreated	1215 / 1226 (1)
Ceramic, glazed	+
Ceramics, unglazed	+
Plastic profiles (unplasticized, e. g. Vinnolit)	1217 / 1227
Copper	-
Melamine resin panels	1216
Brass	-
Natural stone / marble	-

Polyester	+
Polypropylene	-
Cellular concrete	1105
Plaster	1105
PVC unplasticized	1217 / 1227
PVC-soft-foils	1217
Sandstone	-
Tinplate	-
Zinc, galvanised iron	-

1) Upon high exposure to water please contact our Technical Department.

+ = good adherence without primer

- = not suitable

T = Test/pilot test advised

#### Application information:

Due to the many possible influences during and after application, the customer always has to carry out trials first.

Please observe the recommended shelf life which is printed on the packaging.

We recommend to store our products in unopened original packagings dry (< 60 % RH) at temperatures of +15 °C up to +25 °C. If the products are stored and / or transported at higher temperatures / air humidity for longer periods (some weeks), a diminution of durability or a change of material characteristics may arise.

#### Packaging:

	310 ml cartridge	400 ml aluminium foil bag
agate grey	S105-04-C62	on request
anthracite	S105-04-C67	on request
bahamabeige	S105-04-C10	S105-07-C10
basalt	S105-04-C1105	on request
beach-beige	S105-04-C1106	on request
black	S105-04-C04	on request
brown	S105-04-C05	on request
caramel	S105-04-C09	on request
cement-grey no. 31	S105-04-C706	on request
cloud grey	S105-04-C387	on request
fair grey no. 21	S105-04-C501	on request
fair-graphite	S105-04-C1168	on request
flannel grey	S105-04-C72	S105-07-C72
flash grey	S105-04-C787	S105-07-C787
fog	S105-04-C230	S105-07-C230
grey	S105-04-C02	S105-07-C02
grey 15	S105-04-C776	on request
grey-white	S105-04-C70	S105-07-C70
jasmin	S105-04-C08	S105-07-C08
joint-grey	S105-04-C71	S105-07-C71
light-grey	S105-04-C656	on request
manhattan	S105-04-C43	S105-07-C43
middle-brown	S105-04-C15	on request
pale grey	S105-04-C86	S105-07-C86
pergamon	S105-04-C84	on request
platinum grey	S105-04-C52	on request
sand grey 18	S105-04-C2044	on request
sanitary grey	S105-04-C18	S105-07-C18
silk grey	S105-04-C77	S105-07-C77
silver-grey	S105-04-C94	S105-07-C94
silver-grey no. 17	S105-04-C910	on request
snow-white	S105-04-C116	on request
stone grey	S105-04-C79	on request
transparent	S105-04-C00	S105-07-C00
white	S105-04-C01	S105-07-C01
<b>Packaging unit</b>	<b>20</b>	<b>20</b>

**Safety precautions:**

Please observe the material safety data sheet.  
After curing the product is completely odourless.

**Disposal:**

Information about disposal: Please refer to the material safety data sheet.

**Warranty information:**

All information in this publication is based on our current technical knowledge and experience. However, since conditions and methods of use and application of our products are beyond our control, we suggest that you test the product before final use. Information given in this technical data sheet and explanations of OTTO-CHEMIE in connection with this technical data sheet (e.g. service description, reference to DIN regulations etc.) is not to be seen as a warranty. Warranties require a separate written declaration of OTTO-CHEMIE to prove their validity. The characteristics stated in this data sheet define the characteristics of the article broadly and conclusively. Suggestions of use are not to be taken as confirmation of the appropriateness for the recommended intended use. We reserve the right to alter the product, adjusting it according to technical progress and new developments. We are at your disposal both for inquiries as well as specific application problems. If a governmental approval or clearance is necessary for the application of our products, the user is responsible for the obtainment of such. Our recommendations do not excuse the user from the obligation to take into consideration the possibility of infringement of third parties' rights and - if necessary - resolving it. For the rest our general terms and conditions apply, in particular regarding a possible liability for defects. You can find our general terms and conditions on our homepage: <http://www.otto-chemie.de/en/terms-and-conditions>